

E6-CR Glass Fiber

Best Corrosion Resistance Solution for High-Performance Composite Material



E6-CR



Boron-Free Fluorine-Free Glass Fiber



中国巨石股份有限公司
CHINA JUSHI CO., LTD

Company Profile

Our company is a leading provider of software solutions for the financial services industry. We have a proven track record of delivering high-quality products and services to our clients.

Our company is a leading provider of software solutions for the financial services industry.

- We have a proven track record of delivering high-quality products and services to our clients.
- We have a proven track record of delivering high-quality products and services to our clients.
- We have a proven track record of delivering high-quality products and services to our clients.
- We have a proven track record of delivering high-quality products and services to our clients.


Our company is a leading provider of software solutions for the financial services industry. We have a proven track record of delivering high-quality products and services to our clients.

Our company is a leading provider of software solutions for the financial services industry. We have a proven track record of delivering high-quality products and services to our clients.

Our company is a leading provider of software solutions for the financial services industry. We have a proven track record of delivering high-quality products and services to our clients.

Our company is a leading provider of software solutions for the financial services industry. We have a proven track record of delivering high-quality products and services to our clients. Our company is a leading provider of software solutions for the financial services industry. We have a proven track record of delivering high-quality products and services to our clients.

Our company is a leading provider of software solutions for the financial services industry. We have a proven track record of delivering high-quality products and services to our clients. Our company is a leading provider of software solutions for the financial services industry. We have a proven track record of delivering high-quality products and services to our clients. Our company is a leading provider of software solutions for the financial services industry. We have a proven track record of delivering high-quality products and services to our clients.



Contents

E6-CR GLASS FIBER --- Best Corrosion Resistance

E6-CR REINFORCEMENTS --- Excellent Environment Durability

ENVIRONMENTAL PROTECTION --- Become a Model for Clean Production

CUSTOMER AND TECHNICAL SUPPORT ORGANIZATION

GOALS


Best Corrosion Resistance Solution for
High-Performance Composite Materials

To achieve clean production and minimize environmental footprint, Jushi Group successfully developed E6[®] enhanced glass fiber in 2008. With the rapid development of new applications, the design of fiberglass composite parts is becoming more and more demanding, for example, both the manufacturers and end users want products with long-term consistency and reliability. To meet these demands, as well as to meet the technical requirements from corrosion resistance application field, the development of E6-CR glass fiber was successfully completed by Jushi Group and was commercially available since 2012.

E6-CR enhanced glass fiber is a new E-glass fiber with enhanced properties. It combines all the benefits of E6[®] glass fiber with excellent corrosion resistance, thus meeting the requirements of the most demanding applications. E6-CR provides customers with best solutions for corrosion resistance.

E6-CR GLASS FIBER

Excellent Corrosion
Resistance



Compared with typical E-glass fiber, E6-CR offers the following unique benefits:

- Higher chemical stability
- Boron-free fluorine-free, to ensure clean production

E6-CR glass fiber is produced with a unique glass

Material	Chemical Composition	Modulus	Strength	Weight	Volume
E-glass	SiO ₂ 52.0%, Al ₂ O ₃ 1.0%, CaO 16.0%, MgO 1.0%, B ₂ O ₃ 17.0%	70 GPa	2.5 GPa	2.5 g/cm ³	1.0 cm ³
E6-CR	SiO ₂ 52.0%, Al ₂ O ₃ 1.0%, CaO 16.0%, MgO 1.0%, B ₂ O ₃ 17.0%	70 GPa	2.5 GPa	2.5 g/cm ³	1.0 cm ³
E-glass	SiO ₂ 52.0%, Al ₂ O ₃ 1.0%, CaO 16.0%, MgO 1.0%, B ₂ O ₃ 17.0%	70 GPa	2.5 GPa	2.5 g/cm ³	1.0 cm ³
E6-CR	SiO ₂ 52.0%, Al ₂ O ₃ 1.0%, CaO 16.0%, MgO 1.0%, B ₂ O ₃ 17.0%	70 GPa	2.5 GPa	2.5 g/cm ³	1.0 cm ³

Material	Chemical Composition	Modulus	Strength	Weight	Volume
E-glass	SiO ₂ 52.0%, Al ₂ O ₃ 1.0%, CaO 16.0%, MgO 1.0%, B ₂ O ₃ 17.0%	70 GPa	2.5 GPa	2.5 g/cm ³	1.0 cm ³
E6-CR	SiO ₂ 52.0%, Al ₂ O ₃ 1.0%, CaO 16.0%, MgO 1.0%, B ₂ O ₃ 17.0%	70 GPa	2.5 GPa	2.5 g/cm ³	1.0 cm ³
E-glass	SiO ₂ 52.0%, Al ₂ O ₃ 1.0%, CaO 16.0%, MgO 1.0%, B ₂ O ₃ 17.0%	70 GPa	2.5 GPa	2.5 g/cm ³	1.0 cm ³
E6-CR	SiO ₂ 52.0%, Al ₂ O ₃ 1.0%, CaO 16.0%, MgO 1.0%, B ₂ O ₃ 17.0%	70 GPa	2.5 GPa	2.5 g/cm ³	1.0 cm ³

E6-CR REINFORCEMENTS

Excellent Environment Durability

In the future, end-use composite products will operate in even harsher environments and the end-users will expect enhanced durability. Compared with E6®glass fiber, **E6-CR enhanced glass fiber** reinforced composite materials offer better corrosion resistance and temperature endurance, making composite parts more reliable and cost effective.

Superior Mechanical Properties

Test Sample	Property	Standard	E	E6®	E6-CR
Tensile property of impregnated roving, Epoxy resin	Tensile strength (MPa)	ASTM D2343	1900~2000	2500~2700	2500~2700
	Tensile modulus (MPa)	ASTM D2343	73~75	81~83	81~84
1200 g/m ² UD fabric, (tested in 0° direction), Infusion process, Epoxy resin	Tensile strength (MPa)	ISO 527-5	/	1120.6	1125.0
	Tensile modulus (MPa)	ISO 527-5	/	42.6	42.9
	Fiber Volume Content (%)	ISO 1172	/	53.6	54.0
	Tensile strength (MPa)	ISO 14126	/	805.5	810.5
	ensile modulus (GPa)	ISO 14126	/	42.9	43.1
	Fiber Volume Content (%)	ISO 1172	/	54.3	54.4

Chemical Stability

Degradation (% Loss) after boiling in water for 7 days

Sample	Property	Standard	E6®	E6-CR
800g/m ² woven roving	Glass content (%)	ISO 1172	57	57
	Tensile strength (MPa)	GB/T 1447	38.1%	11.4%
Unsaturated polyester	Tensile modulus (GPa)	GB/T 1447	2.8%	1.9%
Hand laid laminates	Flexural strength (MPa)	GB/T 1449	29.5%	22.3%
	Flexural modulus (GPa)	GB/T 1449	13.0%	13.1%

Temperature Resistance



Glass fiber reinforced composites are increasingly used in harsh environments, such as pipes used in oil-field process where it remains at high temperature waste gases. drastic changes in ambient temperature reduce the strength and thus shorten the operating life of composite materials.

The composite samples tested below were dried for 10 days at 180, and then put in an -60 environment for another 10 days. The relative loss of properties after the exposure is shown in the table below.

Sample	Property	Standard	E6®	E6-CR
100g/m ² woven roving	Glass content (%)	ISO 1172	58	58
	Tensile strength (MPa)	GB/T 1447	4.9%	4.5%
Unsaturated polyester	Tensile modulus (GPa)	GB/T 1447	6.6%	6.1%
Hand laid laminates	Flexural strength (MPa)	GB/T 1449	17.0%	15.4%
	Flexural modulus (GPa)	B/T 1449	14.0%	12.8%

ENVIRONMENTAL

PROTECTION





CUSTOMER AND TECHNICAL SUPPORT ORGANIZATION

Offer Best Technical Support

China Jushi possesses world class core technologies and advanced testing and analysis capabilities for glass, organic chemistry, fiberglass and composites. We have established a global network of marketing and technical service professionals to help customers solve problems in materials development and process optimization. We collaborate closely with customers to address market challenges and promote the growth of the composites industry.

We will share with you all the information on **E6-CR** glass fiber reinforcements as well as our considerable knowledge of compounding and molding technology and processes.



Website:

<http://www.jushi.com>

E-mail addresses:

wenzhong.xing@jushi.com	(Glass technology)
zhangyan@jushi.com	(Composites)
qing.wei@jushi.com	(Business cooperation: domestic)
freeman.wang@jushi.com	(Business cooperation: foreign)
services@jushi.com	(Customer service)

★All the data given in this brochure is preliminary and China Jushi reserves the right to update or modify the data without notice.





Add: Tongxiang Economic Development Zone, Zhejiang 314500, China
 International Sales: Tel: +86-573-88136318 Fax: +86-573-88181058
 Domestic Sales: Tel: +86-573-88181016 Fax: +86-573-88136319
 Customer Service: Tel: +86-573-88136325 Fax: +86-573-88136248
 Http://www.jushi.com E-mail: info@jushi.com